


AlN Nano powder datasheet

appearance	off-white powder
Purity	>99%
Fe content	<40ppm
oxygen content	<0.8%
crystal form	hexagonal structure
average particle size	100-500nm
specific surface area	>10m ² /g
apparent density	1.3g/cm ³
processing method	plasma vapor deposition



NaBond Technologies Co., Limited

Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: info@nabond.com