

CuO nanopowder

<u>Average Particle Size</u>	<60nm
<u>BET Specific Surface Area:</u>	>80m ² /g
<u>Content of CuO:</u>	>98%
<u>Content of Ni:</u>	<16ppm
<u>Content of Cl:</u>	<28ppm
<u>Content of SO4:</u>	<70ppm
<u>Content of N:</u>	<40ppm
<u>Content of CO3:</u>	<25ppm
<u>Content of Fe:</u>	<50ppm
<u>Content of Cu2O:</u>	<60ppm

NaBond Technologies Co., Limited

Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: info@nabond.com