

SiB6 Nano powder datasheet

appearance	Black powder
Purity	>99%
crystal form	cubic lattice
average particle size	60nm
specific surface area	35m ² /g
apparent density	0.05g/cm ³
Zeta potential	46.7mV
processing method	plasma vapor deposition

NaBond Technologies Co., Limited

Address: B-204, Ding Tai Feng Hua, Qianhai Road Nanshan, Shenzhen, China 518052

Tel: 86-755-89801091

Fax: 86-755-86058970

<http://www.nabond.com>

email: info@nabond.com